



Weatherstrip Attachment Tape 5933

Technical Data Sheet


April 2009

Supersedes Technical Data Sheet dated August 2004

General Description 3M™ Weatherstrip Attachment Tape 5933 is a 1.14 mm thick, medium-density, gray acrylic foam tape constructed with two different adhesives. The heat-activated adhesive forms an immediate, consistent and durable bond to most Neoprene, PVC and Alcryn® materials. The pressure-sensitive adhesive is characterized by high adhesion and holding strength to many surfaces, including automotive paints and metals. This tape has good conformability and is used to attach weatherstrip and/or gasket seals for automotive and industrial applications.

Shelf Life One year from date of receipt by customer when stored at 4°C - 38°C (40°F - 100°F) and 0-95% relative humidity (RH). The optimum storage conditions are 22°C (72°F) and 50% relative humidity.

Product Construction



Physical Properties

Values shown are typical values not to be used for specification purposes.

Tape thickness (excluding liner)	1.14 mm ± 0.10 mm (0.045 inch ± 0.004 inch)
Tape density (excluding liner)	670 kg/m ³ ± 65 kg/m ³ (42 lb/ft ³ ± 4 lb/ft ³)
Tabbing options	3M™ Tabbing Tape 5400 or 5081

Roll Width and Length

3M™ Weatherstrip Attachment Tapes are available in the following standard widths. Millimeter widths are rounded to the nearest whole numbers (7, 8, 9 mm . . .) and 1/8 inch increments starting with 1/4 inch (0.25, 0.375, 0.50, 0.625 inch . . .).

Minimum widths:
4 mm Levelwound
5 mm Planetary

Roll Width	Roll Width Tolerance	Roll Length (maximum)
Planetary Rolls		
5 - 6 mm (0.197 - 0.236 in.)	+/- 0.40 mm (+/-0.015 in.)	66 meters (72 yards)
6.35 - 9.5 mm (0.25 - 0.375 in.)	+/- 0.40 mm (+/-0.015 in.)	99 meters (108 yards)
10 - 18 mm (0.394 - 0.709 in.)	+/- 0.40 mm (+/-0.015 in.)	132 meters (144 yards)
> 18 mm (> 0.709 in.)	+/- 0.80 mm (+/- 0.031 in.)	132 meters (144 yards)
Levelwound Rolls		
4 - 16 mm (0.157 - 0.630 in.)	+/- 0.40 mm (+/-0.015 in.)	900 meters (984 yards)

Technical Data Sheet


3M™ Weatherstrip Attachment Tape 5933

Page 2


Performance Properties

90° Peel Adhesion

Typical performance of 3M™ Weatherstrip Attachment Tape 5933 is shown below. Peel values depend on the composition and cross-section of a particular weatherstrip. These values are for reference only.



90° Peel Adhesion



Contact Information

The information provided in this technical document is intended as a guide for this product. For more information or help in selecting a 3M product for an application, please contact 3M HELPS at 1-888-3M HELPS (1-888-364-3577).

Regulatory

IMDS# 6179555. This is a published material entry on www.mdssystem.com.

Alcryn® is a Registered Trademark of Advanced Polymer Alloys.

3M is a Trademark of 3M Company.

Technical Information: The technical information, recommendations and other statements contained in this document are based upon tests or experience that 3M believes are reliable, but the accuracy or completeness of such information is not guaranteed.

Product Use: Many factors beyond 3M's control and uniquely within user's knowledge and control can affect the use and performance of a 3M product in a particular application. Given the variety of factors that can affect the use and performance of a 3M product, user is solely responsible for evaluating the 3M product and determining whether it is fit for a particular purpose and suitable for user's method of application.

Warranty, Limited Remedy, and Disclaimer: Unless an additional warranty is specifically stated on the applicable 3M product packaging or product literature, 3M warrants that each 3M product meets the applicable 3M product specification at the time 3M ships the product. 3M MAKES NO OTHER WARRANTIES OR CONDITIONS, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OR CONDITION OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE OR ANY IMPLIED WARRANTY OR CONDITION ARISING OUT OF A COURSE OF DEALING, CUSTOM OR USAGE OF TRADE. If the 3M product does not conform to this warranty, then the sole and exclusive remedy is, at 3M's option, replacement of the 3M product or refund of the purchase price.

Limitation of Liability: Except where prohibited by law, 3M will not be liable for any loss or damage arising from the 3M product, whether direct, indirect, special, incidental or consequential, regardless of the legal theory asserted, including warranty, contract, negligence or strict liability. (make sure enough room around 3M logo)

3M

Automotive Division

3M Center, Building 223-1S-02
St. Paul, MN 55144-1000
www.3M.com/autosolutions

© 3M 2009
75-3468-7556-0
Printed in the U.S.A.



ISO/TS 16949:2002
File No. A2109